



AFRL-ML-WP-TP-2007-522

**PHOTOEXCITED-CARRIER-INDUCED REFRACTIVE-
INDEX CHANGE IN SMALL BAND-GAP
SEMICONDUCTORS (PREPRINT)**

Z.G. Yu, S. Krishnamurthy, and Shekhar Guha

Hardened Materials Branch

Survivability and Sensor Materials Division

JANUARY 2006

Approved for public release; distribution unlimited.

See additional restrictions described on inside pages

STINFO COPY

**AIR FORCE RESEARCH LABORATORY
MATERIALS AND MANUFACTURING DIRECTORATE
WRIGHT-PATTERSON AIR FORCE BASE, OH 45433-7750
AIR FORCE MATERIEL COMMAND
UNITED STATES AIR FORCE**

NOTICE AND SIGNATURE PAGE

Using Government drawings, specifications, or other data included in this document for any purpose other than Government procurement does not in any way obligate the U.S. Government. The fact that the Government formulated or supplied the drawings, specifications, or other data does not license the holder or any other person or corporation; or convey any rights or permission to manufacture, use, or sell any patented invention that may relate to them.

This report was cleared for public release by the Air Force Research Laboratory Wright Site (AFRL/WS) Public Affairs Office and is available to the general public, including foreign nationals. Copies may be obtained from the Defense Technical Information Center (DTIC) (<http://www.dtic.mil>).

AFRL-ML-WP-TP-2007-522 HAS BEEN REVIEWED AND IS APPROVED FOR PUBLICATION IN ACCORDANCE WITH ASSIGNED DISTRIBUTION STATEMENT.

*//Signature//

SHEKHAR GUHA, Ph.D.
Agile IR Limiters
Exploratory Development
Hardened Materials Branch

//Signature//

MARK S. FORTE, Acting Chief
Hardened Materials Branch
Survivability and Sensor Materials Division

//Signature//

TIM J. SCHUMACHER, Chief
Survivability and Sensor Materials Division

This report is published in the interest of scientific and technical information exchange, and its publication does not constitute the Government's approval or disapproval of its ideas or findings.

*Disseminated copies will show “//Signature//” stamped or typed above the signature blocks.

REPORT DOCUMENTATION PAGE				Form Approved OMB No. 0704-0188	
<p>The public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Department of Defense, Washington Headquarters Services, Directorate for Information Operations and Reports (0704-0188), 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to any penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number. PLEASE DO NOT RETURN YOUR FORM TO THE ABOVE ADDRESS.</p>					
1. REPORT DATE (DD-MM-YY) January 2006		2. REPORT TYPE Journal Article Preprint		3. DATES COVERED (From - To)	
4. TITLE AND SUBTITLE PHOTOEXCITED-CARRIER-INDUCED REFRACTIVE-INDEX CHANGE IN SMALL BAND-GAP SEMICONDUCTORS (PREPRINT)				5a. CONTRACT NUMBER In-house	
				5b. GRANT NUMBER	
				5c. PROGRAM ELEMENT NUMBER 62102F	
6. AUTHOR(S) Z.G. Yu and S. Krishnamurthy (SRI International) Shekhar Guha (AFRL/MLPJ)				5d. PROJECT NUMBER 4348	
				5e. TASK NUMBER RG	
				5f. WORK UNIT NUMBER M08R1000	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) SRI International 332 Waverly Street Menlo Park, CA 94025				8. PERFORMING ORGANIZATION REPORT NUMBER AFRL-ML-WP-TP-2007-522	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) Air Force Research Laboratory Materials and Manufacturing Directorate Wright-Patterson Air Force Base, OH 45433-7750 Air Force Materiel Command United States Air Force				10. SPONSORING/MONITORING AGENCY ACRONYM(S) AFRL/MLPJ	
				11. SPONSORING/MONITORING AGENCY REPORT NUMBER(S) AFRL-ML-WP-TP-2007-522	
12. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release; distribution unlimited.					
13. SUPPLEMENTARY NOTES Journal article submitted to Optics Express Journal. The U.S. Government is joint author of this work and has the right to use, modify, reproduce, release, perform, display, or disclose the work. PAO Case Number: AFRL/WS 06-0327, 07 Feb 2006.					
14. ABSTRACT Using accurate band structures of InAs, InSb, and two Hg _{1-x} Cd _x Te alloys, we calculate the change in refractive index caused by the photoexcited electrons and holes. Both free-carrier absorption (FCA) and one-photon absorption are considered. Contrary to current assumptions, we find that the change in refractive index varies nonlinearly with the density of photoexcited carriers and that the FCA may have a significant contribution to the refractive-index change in materials like InAs, where the energy difference between the heavy-hole and light-hole bands is small because of a weak spin-orbit coupling.					
15. SUBJECT TERMS Refractive Index, Photoexcited Carrier, One-Photon Absorption, Free-Carrier Absorption					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT: SAR	18. NUMBER OF PAGES 18	19a. NAME OF RESPONSIBLE PERSON (Monitor) Shekhar Guha 19b. TELEPHONE NUMBER (Include Area Code) N/A
a. REPORT Unclassified	b. ABSTRACT Unclassified	c. THIS PAGE Unclassified			

Photoexcited-carrier-induced refractive-index change in small band-gap semiconductors

· Z. G. Yu and S. Krishnamurthy
SRI International, Menlo Park, CA 94025

Shekhar Guha
Wright-Patterson AFB, Dayton, Ohio 45433

Abstract

Using accurate band structures of InAs, InSb, and two $\text{Hg}_{1-x}\text{Cd}_x\text{Te}$ alloys, we calculate the change in refractive index caused by the photoexcited electrons and holes. Both free-carrier absorption (FCA) and one-photon absorption are considered. Contrary to current assumptions, we find that the change in refractive index varies nonlinearly with the density of photoexcited carriers and that the FCA may have a significant contribution to the refractive-index change in materials like InAs, where the energy difference between the heavy-hole and light-hole bands is small because of a weak spin-orbit coupling.

Key words: refractive index, photoexcited carriers, one-photon absorption, and free-carrier absorption

Introduction

Semiconductor materials such as InSb, InAs and HgCdTe are used in opto-electronic applications including quantum cascade lasers, terahertz generation, and saturable absorbers [1-2]. These applications involve generation of high levels of charge carriers that render it important to understand the effect of photoexcited carriers on the material optical properties. In addition, high-intensity light propagation in semiconductors can be strongly affected by the generation of a high density of photoexcited carriers. The incident light creates electron-hole pairs, some of which recombine through a variety of mechanisms including the Auger, radiative, and Shockley-Read-Hall (SRH) processes. Not all electron-hole pairs will recombine before the entry of the next stream of photons, and the excess excited carriers will alter the photon absorption both across the fundamental gap and between the valence bands. As a result, the refractive index deviates from the value at equilibrium. Although there are number of studies to accurately calculate the absorption and carrier relaxation in semiconductors, only simplified models that use effective mass bandstructures, the Boltzmann distribution for the carriers, and one-photon absorption (OPA) across the band gap are currently being employed in the evaluation of refractive index changes [3-7]. The contribution from free carrier absorption (FCA) is not included in these studies. These calculations predict that the change in refractive index varies linearly with the carrier density and increases with lattice temperature.

In this paper, we use full band structures and Fermi-Dirac (FD) statistics for photo-excited carriers to systematically calculate the change in refractive index arising from both OPA and FCA in four direct band-gap semiconductors: two having band gaps less than 0.21 eV (InSb and $\text{Hg}_{0.762}\text{Cd}_{0.238}\text{Te}$) and two having a band gap approximately 0.35 eV (InAs and $\text{Hg}_{0.656}\text{Cd}_{0.344}\text{Te}$). The results from this accurate calculation differ from the existing results not only in the magnitude, but also in the trend. The calculated change in refractive index (a) varies highly nonlinearly with the excess carrier density in the two smaller band gap materials but almost linearly in the two larger band gap materials, (b) has a considerable contribution from FCA in InAs, where the spin-orbit (SO) splitting is small.

Formalism:

The photoexcited carriers in the conduction and valence bands modify the absorption spectrum, which results in a change in the refractive index through the Kramers-Kronig relation between the real part of the refractive index, n_1 , and the absorption coefficient, $\alpha(\omega)$,

$$n_1(\omega) - 1 = \frac{c}{\pi} P \int_0^\infty \frac{\alpha(\omega') d\omega'}{\omega'^2 - \omega^2} \quad (1)$$

where c is the speed of light, ω is the angular frequency, and P indicates principle value of the integral. The refractive index change, Δn_1 , arising from the excess carriers, can be calculated from [8]

$$\Delta n_1(\omega) = \frac{c}{\pi} P \int_0^\infty \frac{\alpha(\omega', \Delta N) - \alpha(\omega', 0) d\omega'}{\omega'^2 - \omega^2} \quad (2)$$

where $\alpha(\omega', \Delta N)$ and $\alpha(\omega', 0)$ are the absorption coefficients at angular frequency of ω' in the presence of photoexcited electron-hole pairs with the density of ΔN and in equilibrium, respectively.

The absorption coefficient is related to the imaginary part of the dielectric function, $\epsilon_2(\omega)$, via $\alpha(\omega) = \frac{\omega \epsilon_2(\omega)}{n_1(\omega) c}$. For a small change in refractive index, $n_1(\omega)$ in this relation can be replaced by $n_1^0(\omega)$, which is the refractive index for the system in equilibrium. The absorption change can then be written in terms of the change in the dielectric function,

$$\alpha(\omega, \Delta N) - \alpha_0(\omega) = \frac{\omega}{n_1^0(\omega) c} [\epsilon_2(\omega, \Delta N) - \epsilon_2(\omega, 0)] \quad (3)$$

where $\epsilon_2(\omega, 0)$ and $\epsilon_2(\omega, \Delta N)$ are the imaginary part of the dielectric function for the system in equilibrium and in the presence of additional electron-hole pairs density of ΔN , respectively.

Among many absorption processes the FCA and OPA are most sensitive to the carrier occupation in a small band-gap material. The OPA excites an electron from the valence band into the conduction band when the photon has energy greater than the band gap. To achieve this

interband transition, the initial state in the valence band must be occupied and the final state in the conduction band must be vacant. The photoexcited carriers change the occupation in both conduction and valence bands when compared to the system in equilibrium and thus modify the OPA. When the energy of a photon is not large enough to enable the valence band to conduction band transitions, the carriers can still absorb the photon through intra-band transitions (with the help of phonons) and inter-valence band transitions, commonly known as FCA. Since both these processes are proportional to the number of carriers, the photoexcited carriers will modify the FCA spectrum as well. Here we calculate the change in dielectric function arising from the OPA and FCA by electrons and holes using accurate band structures and wave functions from a long-range tight-binding Hamiltonian [7]. It should be noted from Eqs. (2) and (3) that the dielectric function needs to be computed over a very large frequency range even if we are interested in calculating the Δn_1 near the band edge frequencies. In addition, a careful numerical evaluation of the integral in Eq. (2) is required because of the singularity in the integrand.

Results and discussions

To test the accuracy of the band structures and dipole matrix elements used in our calculations, we have computed the OPA coefficients in InSb and InAs and found those to be in excellent agreement with the measured values. The dielectric function and the change in the refractive index are then calculated for the two materials with band gap E_g of 0.35 eV -- InAs and $\text{Hg}_{0.656}\text{Cd}_{0.344}\text{Te}$, and the two smaller band-gap materials—InSb ($E_g=0.173$ eV) and $\text{Hg}_{0.762}\text{Cd}_{0.238}\text{Te}$ ($E_g=0.206$ eV). The spectra of $n^0_1(\omega)$ used in our calculations are from the literature [10-13].

Figure 1 shows the calculated change in refractive index as a function of wavelength due to the FCA and OPA in InSb at two densities of photoexcited electron-hole pairs --- $\Delta N=10^{16}$ and 10^{17} cm^{-3} . We see that the FCA contribution depends weakly on the wavelength. However, the OPA contribution shows a steep change near the band gap. This variation can be easily understood from Eq. (2). In the presence of photoexcited carriers, the band edge states are filled and the joint density of states of electrons and holes available for absorption decreases and the OPA is reduced. Thus the numerator of the integrand in Eq. (2) is either zero (for $\omega' < \omega_g$) or negative (for $\omega' > \omega_g$) with ω_g being the band gap frequency. When the frequency ω crosses ω_g , the denominator of the integrand changes sign and, consequently, $\Delta n_1(\omega)$ changes sign.

The calculated value of Δn_1 at $\lambda = 9.5 \mu\text{m}$ is shown in Fig. 2 as a function of photoexcited carrier density in InSb and $\text{Hg}_{0.762}\text{Cd}_{0.238}\text{Te}$. We see that in both materials the OPA contribution dominates over the FCA contribution to the Δn_1 . Interestingly, the FCA contribution is positive, which is opposite of the OPA contribution at this wavelength. Similarly calculated results at $\lambda = 4.8 \mu\text{m}$ for the larger band-gap materials — InAs and $\text{Hg}_{0.656}\text{Cd}_{0.344}\text{Te}$ — are plotted in Fig. 3. In this case, both FCA and OPA reduce the refractive index. Although both materials have the same band gap, in the HgCdTe alloy the dominant contribution is from the OPA, whereas in InAs both FCA and OPA have comparable contributions. To understand the different level of contribution of FCA to the refractive-index change, we plot the FCA cross section σ , as a function of wavelength in Fig. 4 for these two materials. The numerator of the integrand in Eq. (2) for the FCA process is proportional to this cross section and the FCA contribution to Δn_1 at a photon wavelength λ is roughly proportional to the difference in the areas below and above that λ in Fig. 4. We see that the absorption for wavelengths below $\lambda = 4.8 \mu\text{m}$ is negligible in InAs, but is significant in the HgCdTe alloy. Owing to a larger cancellation, the FCA contribution is smaller in the HgCdTe alloy. We explore further to understand the origin of the difference in the absorption spectrum of Fig. 4. In our calculations we found that most of the FCA arises from the transitions of electrons from the light-hole to the heavy-hole bands. Hence the different FCA spectra can be understood from the valance band structures in the two materials. We plot in Fig. 5 the energy difference between the heavy-hole and the light-hole valence bands as a function of wave vector \mathbf{k} in symmetry directions for InAs and $\text{Hg}_{0.656}\text{Cd}_{0.344}\text{Te}$. In both cases the energy difference increases rapidly at small values of \mathbf{k} , but saturates at 0.25 eV as the wave vector increases further in InAs. This small saturation value can be attributed to the weak SO coupling (0.38 eV) in InAs, which repels the light-hole valence band closer to the heavy-hole valence band. Absorption of photon with a larger energy than this saturation value is not possible. In the HgCdTe alloy, however, a relatively larger SO coupling (0.95 eV) allows the light hole band to move farther away from the heavy hole band, resulting in absorption at shorter wavelengths. Hence the relative contribution from OPA and FCA depend critically on the subtle details of the band structures.

The sum of the FCA and OPA induced change in refractive index, calculated at $4.8 \mu\text{m}$ for large gap materials and at $9.5 \mu\text{m}$ for small gap materials, is shown in Fig. 6 as a function of the density of photoexcited electron-hole pairs. Clearly the variation is nonlinear for the two

smaller band-gap materials. An accurate fit to the total change indicated that variation is nonlinear even for the larger band-gap materials. Excellent fits to all four materials are obtained by using a functional form $\Delta n_i = a(1 - e^{-b\Delta N})$. Only for small $\Delta N (< 10^{16} \text{ cm}^{-3})$, does the refractive index change linearly with ΔN . The fitted values of a and b are given in Table I.

It is interesting to estimate the effect of temperature on the OPA induced change in the refractive index. In our calculation with FD statistics and full band structures, the excess carrier induced change in OPA is nearly temperature independent. However, for example, the band gap in InSb changes from 0.173 eV at 300K to 0.234 eV at 77K. Since the contribution arising from OPA is nonzero only when $\omega' > \omega_g$, the denominator of the integrand in Eq. (2) is larger at $T=77$ K than at 300K, resulting in smaller change in the index. This conclusion is in contradiction with the previous studies [5,6] which used simplified band structures and Boltzmann distribution.

Conclusions

In conclusion, we have calculated the change in refractive index arising from both the OPA and the FCA using full band structures for four materials, InSb, $\text{Hg}_{0.762}\text{Cd}_{0.238}\text{Te}$, InAs, and $\text{Hg}_{0.656}\text{Cd}_{0.344}\text{Te}$. We focus on the refractive-index change at $\lambda=9.5 \mu\text{m}$ for the first two materials that have band gaps less than 0.21 eV and at $\lambda=4.8 \mu\text{m}$ for the last two materials that have a band gap of 0.35 eV. The calculations show that the FCA contribution is not negligible and is comparable to the OPA contribution in InAs that has a small SO splitting. The calculated dependence of the change in refractive index on the density of photoexcited electron-hole pairs is strongly nonlinear in InSb and $\text{Hg}_{0.762}\text{Cd}_{0.238}\text{Te}$ and moderately nonlinear in InAs and $\text{Hg}_{0.656}\text{Cd}_{0.344}\text{Te}$. Furthermore, the change in refractive index for InSb due to the OPA is smaller at lower temperatures than at room temperature because of a larger band gap at low temperatures.

This work was supported by the Air Force Materials Laboratory at Wright-Patterson AFB through Anteon Corporation contract (USAF-5400-03-SC-0006).

References

1. W. S. Pelouch and L. A. Schlie, "Ultrafast carrier dynamics and saturable absorption in HgCdTe", Appl. Phys. Lett. **68**, 1389-1391 (1996).
2. S. Kono, P. Gu, M. Tani, and K. Sakai, "Temperature dependence of terahertz radiation from n-type InSb and n-type InAs surfaces", Appl. Phys. B **71**, 901-904 (2000).
3. For a review see, D.M. Kovsh, S. Yong, D.J. Hagan, and E. Van Stryland, "Nonlinear Optical Liquid for Power Limiting", SPIE **3472**, 163-177 (1998).
4. D.H. Auston, S. McAfee, C.V. Shank, E.P. Ippen, and O. Teschke, "Picosecond spectroscopy of semiconductors", Solid State Electron. **21**, 147-150 (1978).
5. D. A. B. Miller, C. T. Seaton, M. E. Prise, and S. D. Smith, "Band-gap-resonant nonlinear refraction in III-V semiconductors", Phys. Rev. Lett. **47**, 197-200 (1981).
6. E. W. van Stryland, Y.Y. Wu, D.J. Hagan, M.J. Soileau, K. Mansour, "Optical limiting with semiconductors", J. Opt. Soc. Am. **5**, 1980-1989 (1988).
7. P. P. Paskov and K. R. Koynov, "A theoretical analysis of absorption and refractive index changes in optically excited $\text{In}_{1-x}\text{Ga}_x\text{Sb}$ ", Semicond. Sci. Technol. **9**, 1584-1590 (1994).
8. J. I. Pankove, *Optical Processes in Semiconductors* (Dover, New York, 1975), pp 90.
9. A.B. Chen and A. Sher, *Semiconductor Alloys* (Plenum, 1995), Ch. 5.
10. Z. Kucera, "Dispersion of the refractive index of $\text{Hg}_{1-x}\text{Cd}_x\text{Te}$ ", Phys. Status Solidi A, **100**, 659-665 (1987).
11. S. Rolland, "Dielectric constant and refractive index of HgCdTe" in *Properties of Narrow Gap Cadmium-Based Compounds*, P. Capper, ed (INSPEC, IEE, London, 1994). Pp 80-85.
12. E.D. Palik and R.T. Holm, "Indium Arsenide" in *Handbook of Optical Constants of Solids*, D. Palik, ed (Academic, San Diego, 1998) pp 479-489.
13. R.T. Holm, "Indium Antimonide" in *Handbook of Optical Constants of Solids*, D. Palik, ed (Academic, San Diego, 1998) pp 490-502.

Table 1: Fit parameters to obtain the calculated change in refractive index at 300K

Parameters	InAs	Hg _{1-x} Cd _x Te (x=0.344)	InSb	Hg _{1-x} Cd _x Te (x=0.238)
a	0.13067	0.14536	0.077854	0.12091
b	8.1952e-19	7.079e-19	2.9875e-18	1.6804e-18

Figure Captions:

Figure 1: Refractive-index change due to the FCA and OPA as a function of the photon wavelength in InSb with $\Delta N = 10^{16}$ and 10^{17} cm^{-3} at room temperature.

Figure 2: Refractive-index change at $\lambda = 9.5 \mu\text{m}$ due to the FCA and OPA as a function of ΔN in InSb and $\text{Hg}_{0.762}\text{Cd}_{0.238}\text{Te}$ at room temperature.

Figure 3: Refractive-index change at $\lambda = 4.8 \mu\text{m}$ due to the FCA and OPA as a function of ΔN in InAs and $\text{Hg}_{0.656}\text{Cd}_{0.344}\text{Te}$ at room temperature.

Figure 4: Cross section of the FCA σ as a function of the photon wavelength in InAs and $\text{Hg}_{0.656}\text{Cd}_{0.344}\text{Te}$ at room temperature.

Figure 5: Energy difference between the heavy-hole and light-hole valence bands as a function of wave vector for InAs and $\text{Hg}_{0.656}\text{Cd}_{0.344}\text{Te}$ at room temperature.

Figure 6: Total change in the refractive index Δn_I at $\lambda = 4.8 \mu\text{m}$ for InSb and $\text{Hg}_{0.762}\text{Cd}_{0.238}\text{Te}$ and at $\lambda = 9.5 \mu\text{m}$ for InAs and $\text{Hg}_{0.656}\text{Cd}_{0.344}\text{Te}$ as a function of ΔN at room temperature.




Figure 1 Yu et al




Figure 2 Yu et al




Figure 3 Yu et al




Figure 4 Yu et al




Figure 5 Yu et al




Figure 6 Yu et al

